



US009410006B2

(12) **United States Patent**
Haraguchi et al.

(10) **Patent No.:** **US 9,410,006 B2**
(45) **Date of Patent:** **Aug. 9, 2016**

(54) **FLUORINE-CONTAINING HIGHLY
BRANCHED POLYMER AND RESIN
COMPOSITION CONTAINING THE SAME**

(75) Inventors: **Masayuki Haraguchi**, Funabashi (JP);
Motonobu Matsuyama, Funabashi (JP);
Masaaki Ozawa, Funabashi (JP); **Misao**
Miyamoto, Tokyo (JP)

(73) Assignee: **NISSAN CHEMICAL INDUSTRIES,
LTD.**, Tokyo (JP)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 898 days.

(21) Appl. No.: **13/322,722**

(22) PCT Filed: **May 31, 2010**

(86) PCT No.: **PCT/JP2010/059192**

§ 371 (c)(1),
(2), (4) Date: **Feb. 2, 2012**

(87) PCT Pub. No.: **WO2010/137724**

PCT Pub. Date: **Dec. 2, 2010**

(65) **Prior Publication Data**

US 2012/0135206 A1 May 31, 2012

(30) **Foreign Application Priority Data**

May 29, 2009	(JP)	2009-131608
Feb. 16, 2010	(JP)	2010-031879
Mar. 10, 2010	(JP)	2010-053392
Apr. 30, 2010	(JP)	2010-105541

(51) **Int. Cl.**
B32B 3/00 (2006.01)
C08F 8/18 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **C08F 220/22** (2013.01); **C08F 2/48**
(2013.01); **C08F 220/18** (2013.01); **C08L 67/04**
(2013.01);

(Continued)

(58) **Field of Classification Search**

USPC 428/195.1; 526/245
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,235,013	A *	8/1993	Ito et al.	526/245
2007/0032615	A1 *	2/2007	Sato	526/82

FOREIGN PATENT DOCUMENTS

JP	01-289817	*	11/1989
JP	A-1-289817		11/1989

(Continued)

OTHER PUBLICATIONS

Sato et al., "Initiator-Fragment Incorporation Radical Polymeriza-
tion of Divinylbenzene in the Presence of Glyoxylic Oxime Ether:
Formation of Soluble Hyperbranched Polymer," Journal of Polymer
Science: Part A: Polymer Chemistry, 2003, pp. 3038-3047, vol. 41.

(Continued)

Primary Examiner — Peter D Mulcahy

Assistant Examiner — Henry Hu

(74) *Attorney, Agent, or Firm* — Oliff PLC

(57) **ABSTRACT**

It is an object to provide a compound that can provide a
molded article and a coating film excellent not only in solu-
bility in an organic solvent, but also in miscibility with/dis-
persibility in a matrix resin, causing no aggregation in a
matrix resin, excellent in surface modification property, and
having high transparency. A fluorine-containing highly
branched polymer obtained by polymerizing a monomer A
having two or more radical polymerizable double bonds in the
molecule thereof with a monomer B having a fluoroalkyl
group and at least one radical polymerizable double bond in
the molecule thereof in the presence of a polymerization
initiator C in a content of 5% by mol or more and 200% by
mol or less, based on the total molar amount of the monomer
A and the monomer B; and a resin composition comprising
the polymer.

14 Claims, 38 Drawing Sheets

